lassic crest[®]

Production Considerations

STORAGE / HANDLING Papers need to acclimate to pressroom conditions at least 24 hours before opening. Pressroom humidity should be in a range of 40-55% at 70-75°F. Once open, rewrap

unused product.

PREPRESS As a general rule, imagery should be adjusted in prepress to compensate for the

additional 5-15% tone value increase that will occur. The precise amount of undercolor

removal is image-specific. Total area coverage should not exceed 320%.

INK / PRINTING The use of opaque light inks on dark stocks may require an in-line double pass.

Metallic inks work well and deliver successful results. Anticipate a dry-back of 5 to 7

density points.

VARNISH Low solvent (0-5%) varnish can be used as a surface protector; it will not alter nor

enhance the appearance of CLASSIC CREST® Papers. Your ink supplier is the

best resource.

AQUEOUS Aqueous coating can be used as a surface protector; it will not alter nor enhance the COATING

appearance of CLASSIC CREST Papers. Most printers will only use aqueous coating on heavier weight stocks and only with a special formulation for uncoated papers to avoid

possible paper curl. Pretesting is necessary. Your ink supplier is the best resource.

EMBOSSING Writing, Text and Cover weights emboss and deboss beautifully. The uniform

formation of CLASSIC CREST Papers lends itself to perfectly registered embossing.

ENGRAVING Engraving inks need no special treatment. Best results come with a female plate of

> .064 gauge copper and handcut male counter plate of 24-ply counter board applied with 2,000-4,000 pounds of pressure. Pressure range is dependent upon complexity of

> copy. Precision when cutting a counter requires less pressure and enhances the image.

FOIL STAMPING We recommend the use of wax-free litho inks when combining offset lithography and

foil stamping to ensure the best results and the maximum adhesion of foil to ink. For

best results, stamp directly onto the paper.

THERMOGRAPHY No special considerations are needed.

NON-IMPACT CLASSIC CREST Writing and Text in all finishes are guaranteed for laser and ink

PRINTING jet printing.

DIGITAL Our Universal Digital Finish is compatible with all digital presses. For more information **PRINTING**

on digital printing and presses visit: neenahpaper.com/digital



Production Considerations (Continued)

FOLDING / A letterpress channel score parallel to the grain direction is recommended to ensure a SCORING smooth crease. Always pretest with heavier weight covers and double thick covers.

TRIMMING / A sharp blade will ensure a clean cut through the stock; a dull blade could tear DIE-CUTTING the stock.

BINDING Binding should be parallel to the grain direction to prevent moisture buckling and

minimize wear on the crease.